

Products	Tg [oC]	Mw	Application
MARCOATM CH460	~70	14,000	MARCOATM CH460 is a high molecular weight solid polyester resin that provides excellent corrosion resistance for appliance primer in coil coating systems.
MARCOATM CH462	~60	15,000	MARCOATM CH462 is a high molecular weight solid polyester resin with high acid resistance and flexibility to formulate interior can coatings.
MARCOATM CH470	~70	17,000	MARCOATM CH470 is a high molecular weight solid polyester resin that provides both, hardness and flexibility for can coating systems.
MARCOATM CH488	~89	15,000	MARCOATM CH488 is a high molecular weight solid polyester resin with high reactivity and excellent acid resistance for interior can coating systems.
MARCOATM CH489	~89	15,000	MARCOATM CH489 is a high molecular weight solid polyester resin with high reactivity and excellent acid resistance for interior can coating systems.
MARCOATM CH491	~102	15,000	MARCOATM CH491 is a high molecular weight solid polyester resin with a high glass transition temperature and excellent acid resistance for interior can coating systems.
MARCOATM CH492	~104	15,000	MARCOATM CH492 is a high molecular weight solid polyester resin with a high glass transition temperature and excellent acid resistance for interior can coating systems.
MARCOATM CH497	~92	15,000	MARCOATM CH497 is a high molecular weight solid polyester resin with a high glass transition temperature and solubility in a broad range of organic solvents for interior can coating systems.
MARCOATM CH541	~47	16,000	MARCOATM CH541 is a high molecular weight solid polyester resin with excellent processibility and deep drawing for a broad range of coil and can coating systems.
MARCOATM CH550	~52	18,000	MARCOATM CH550 is a high molecular weight solid polyester resin with excellent processibility and deep drawing for a broad range of coil and can coating systems.
MARCOATM CH554	~52	15,000	MARCOATM CH554 is a high molecular weight solid polyester resin with good reactivity with phenolic resins to formulate interior can coatings.
MARCOATM CH563	~65	20,000	MARCOATM CH563 is a high molecular weight solid polyester resin with high reactivity for appliance primer in coil coatings and deep drawing can coatings.
MARCOATM CL150	~52	3,000	MARCOATM CL150 is a medium to low molecular weight solid polyester resin with excellent pigment dispersibility for appliance primer in coil coatings and can coatings.
MARCOATM CL151	~58	3,000	MARCOATM CL151 is a medium to low molecular weight solid polyester resin with high curing density for appliance primer in coil coatings and can coatings.

Products	Tg [oC]	Mw	Application
MARCOATM CL250	~58	5,000	MARCOATM CL250 is a medium to low molecular weight solid polyester resin with excellent hardness and stain resistance in a broad range of coil coatings applications, as well as, can coatings.
MARCOATM CL270	~78	6,000	MARCOATM CL270 is a medium to low molecular weight solid polyester resin to improve flexibility and hardness for solvent-borne can and coil coatings.
MARCOATM CL271	~71	4,500	MARCOATM CL271 is a medium to low molecular weight solid polyester resin with high curing density and excellent adhesion to aluminum for can coatings applications.
MARCOATM CL331	~38	9,000	MARCOATM CL331 is a medium to low molecular weight solid polyester resin with outstanding corrosion resistance for solvent-borne coil coating systems.

¹ Typical values, not for specification purposes